

## LEGA ALLUMINIO

UNI EN 1706 AC 43100 GAS 10 [AC-ALSi10Mg]

Composition in % [mass fraction]			Tensile strength	Proof strength	Elongation	Brinell hardness
Element	min.	MAX.	Rm MPa min.	Rp0,2 MPa min.	A % min.	HBW min.
Si	9,0	11,0	150	80	2	50
Fe	–	0,55				
Cu	–	0,10				
Mn	–	0,45				
Mg	0,20	0,45				
Cr	–	–				
Ni	–	0,05				
Zn	–	0,10				
Pb	–	0,05				
Sn	–	0,05				
Ti	–	0,15				
Al	Remainder					

### Fonderia Caglioni srl

Sede Legale  
Sedi Operative

Via Aldo Moro, 3 — 24050 Orio al Serio (BG)  
Via Aldo Moro, 3-14 — 24050 Orio al Serio (BG)  
T +39 035 4522140 — E-mail info@fonderiacaglioni.it  
C.F./P.IVA 01486010166 — Reg. Imp. BG 23092 - R.E.A. 211939 — Cap. Soc. € 49.400 i.v.

[www.fonderiacaglioni.it](http://www.fonderiacaglioni.it)