

## LEGA RAME - STAGNO [BRONZO]

UNI EN 1982 CC493K RG7 [CuSn7Zn4Pb7-C]

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	Rm MPa min.	Rp0,2 MPa min.	A % min.	HBW min.
Cu (a)	81,0	85,0	230	120	15	60
Ni	–	2,0				
P	–	0,10				
Pb	5,0	8,0				
Sn	6,0	8,0				
Zn	2,0	5,0				
Al	–	0,01				
Fe	–	0,2				
S	–	0,10				
Sb	–	0,3				
Si	–	0,01				

(a) Including nickel

### Fonderia Caglioni srl

Sede Legale  
Sedi Operative

Via Aldo Moro, 3 — 24050 Orio al Serio (BG)  
Via Aldo Moro, 3-14 — 24050 Orio al Serio (BG)  
T +39 035 4522140 — E-mail [info@fonderiacaglioni.it](mailto:info@fonderiacaglioni.it)  
C.F./P.IVA 01486010166 — Reg. Imp. BG 23092 - R.E.A. 211939 — Cap. Soc. € 49.400 i.v.

[www.fonderiacaglioni.it](http://www.fonderiacaglioni.it)