

## LEGA RAME - STAGNO [BRONZO]

ASTM B584 C92200

Composition in % [mass fraction]			Tensile strength	0,2 % proof strength	Elongation	Brinell hardness
Element	min.	MAX.	<i>R<sub>m</sub></i> MPa min.	<i>R<sub>p0,2</sub></i> MPa min.	<i>A</i> % min.	HBW min.
Cu	86,0	90,0	234	110	22	
Sn	5,5	6,5				
Pb	1,0	2,0				
Zn	3,0	5,0				
Ni	–	1,0				

### Fonderia Caglioni srl

Sede Legale  
Sedi Operative

Via Aldo Moro, 3 — 24050 Orio al Serio (BG)  
Via Aldo Moro, 3-14 — 24050 Orio al Serio (BG)  
T +39 035 4522140 — E-mail [info@fonderiacaglioni.it](mailto:info@fonderiacaglioni.it)  
C.F./P.IVA 01486010166 — Reg. Imp. BG 23092 - R.E.A. 211939 — Cap. Soc. € 49.400 i.v.

[www.fonderiacaglioni.it](http://www.fonderiacaglioni.it)